

Sealing compound

# Triflex Cryl R 238



## Product information

### Applications

Triflex Cryl R 238 is used to seal the slots after laying contact loops (induction loops) in asphalt surfaces.

### Properties

2-component pigmented sealing compound with a polymethyl methacrylate resin (PMMA) base. Triflex Cryl R 238 offers the following features:

- Fast-curing
- Surface levelling
- Fast-curing
- UV-resistant
- Solvent-free
- Weather-resistant
- Waterproof
- Flexible
- Wear-resistant
- Suitable for vehicle traffic
- Withstands high mechanical loads

### Pack size

Drum

Summer	Winter	
15.00 kg	15.00 kg	Triflex Cryl R 238 base resin
0.30 kg	0.60 kg	Triflex Catalyst (3 x / 6 x 0.10 kg)
15.30 kg	15.60 kg	

### Colours

7021 Black grey

### Storage

Can be stored unopened and unmixed for approx. 6 months in a cool, dry place above freezing. Keep container away from direct sunlight when in storage and on the construction site.

### Conditions for use

Triflex Cryl R 238 can be applied at substrate and ambient temperatures between 0 °C and +35 °C. In enclosed spaces, always ensure forced ventilation with a minimum 7-fold air exchange per hour.



### Preparation of the substrate

The substrate must be sound, dry and free of loose or adhesion-reducing particles.

During application, the surface temperature must be at least 3 °C above dew point. Below that, a separating film of moisture can form on the surface to be worked on (DIN 4108-5, table 1). See dew point temperature table.

### Mixing instructions

After thoroughly mixing the base resin, the corresponding catalyst quantity is added to and mixed with a slow-running mixing machine until there are no more lumps. Stirring time at least 2 min.

#### Important note:

Use only Powder Catalyst for mixing.

### Mixing ratio

Temperature range of:

0 °C to +5 °C	15.00 kg base resin + 0.60 kg catalyst
+5 °C to +15 °C	15.00 kg base resin + 0.60 kg catalyst
+15 °C to +35 °C	15.00 kg base resin + 0.30 kg catalyst

### Material consumption

Approx. 1.85 kg/m<sup>2</sup> per mm thickness on a smooth even surface

Sealing compound  
**Triflex Cryl R 238**



## Product information

### Pot life

Approx. 15 min at +20 °C

### Drying time

Rainproof after: approx. 30 min. at +20 °C  
Resistant after: approx. 1 hr. at +20 °C

### Notes on special hazards

See Safety Data Sheet, section 2

### Safety tips

See Safety Data Sheet, sections 7 and 8

### Measures in case of fire or accidents

See Safety Data Sheet, sections 4, 5 and 6

### General notes

We guarantee the consistently high quality of our products. Non-Triflex products must not be used with Triflex systems.

The advice we give in relation to the application of our products is based on extensive development and many years of experience, and is correct to the best of our knowledge. Given the multitude of on-site requirements, under the most varied of conditions, the user is required to test the product's suitability for its respective purpose. Technical information is subject to change without notice in the interests of technical advancement or enhancement of our products.